

*ZHEJIANG KAN SPECIALITIES MATERIAL CO. LTD*



[kanpaper.ru](http://kanpaper.ru)

SPECIFICATION

Heatsealing filter paper for teabag



## 1 Type and technical data

ITEM		UNIT	STANDARD				
			16.5g	17.5g	21g	22g	23g
GSM		g/cm <sup>2</sup>	16,5±0,8	17,5±0,8	21,0±0,8	22,0±0,8	23,0±0,8
Density		g/cm <sup>3</sup>	0.31±0,03	0.32±0,03	0.33±0.03	0.33±0.05	0.34±0.05
Tensile Strength	MD	kN/m	≥0.40	≥0.45	≥0.50	≥0.60	≥0.50
	CD	kN/m	≥0.10	≥0.11	≥0.11	≥0.20	≥0.12
Sealing Strength		kN/m	≥0.10	≥0.10	≥0.10	≥0.105	≥0.105
Air Permeability		cu	≥10000	≥6000	≥5000	≥4000	≥3000
Moisture		%	≤8.0				

Test method: agreement to producers standard for this product.

## 2 Material ingredient

1. Wood pulp – 40%
2. Abaca fiber – 40%
3. PP fiber – 20%

## 3 Requirement for Product Appearance

1. The surface of paper sheet should be equal and plane.
2. The colour should be equal and without obvious difference for the same batch.
3. The edge surface of paper roll should be even, The density of two edges should be same. The paper core should be without distortion.

## **4 SIZE**

1. Roll width of our product can be customized, usually there are 64, 66, 120, 125, 132, 260, 264, 385, 485, 585, 740MM.
2. Roll outer diameter is 450-600mm, which can be customized to the customer's requirement and transportation requirement.
3. The inner diameter of roll core is 76mm.

## **5 Packing**

1. It is sealed in the plastic bag with a few rolls together, and packed in the cotton box 0,45\*0,45\*0,5M.
2. In case for container, it may be put on the pallet and is fixed with film rolling for water proof..

## **6 Shipment**

1. Minimum order - one corrugated box.
2. We will provide palletizing and loading on any form of transport, If necessary.

## **7 Keeping**

1. The warm dry conditions.
2. The shelf life of 3 years from date of manufacture.